



Advantage eCom Kraft

Benefits

- Natural look and feel
- 100% fresh fibre
- High strength properties
- High tear-resistance
- High stiffness
- Excellent runnability

End-uses

- Mailer bags
- eCom FFS
- eGrocery bags



PEFC	FSC*	Food Contact Approvals	Quality Management System	Environmental Management System	Safety Management System
•	•	BfR XXXVI FDA Regulation §§ 176.170 FDA Regulation §§ 176.180	ISO 9001:2015	ISO 14001:2015	ISO 45001:2018

*on demand

Technical Values

Properties		Method	Typical values				
Basis Weight	g/m ²	ISO 536	70	80	90	100	110
Thickness**	µm	ISO 534	105	115	130	140	150
Tensile strength MD	kN/m	ISO 1924-3	6,5	7,4	8,4	9,3	10,2
Tensile strength CD	kN/m	ISO 1924-3	3,9	4,4	5,0	5,5	6,1
Tear strength MD	J/m ²	ISO 1924-3	621	744	837	930	1 023
Tear strength CD	J/m ²	ISO 1924-3	721	824	927	1 030	1 133
Cobb ₆₀	g/m ²	ISO 535	32	32	32	32	32
Burst strength	kPa	ISO 2758	300	350	410	460	510
Roughness Bendtsen TS**	ml/min	ISO 8791-2	780	800	960	1100	1300
Stretch MD	%	ISO 1924-3	2,6	2,6	2,6	2,6	2,6
Density**	kg/m ³		670	675	690	705	710

The table above shows typical values for certain basis weights. The applied testing method standards always refer to the latest version of released version of the standard in reference to the issue date of Technical Data Sheet.

** Average values, not specified

Issued from 01.01.2022,
latest version available on
www.mondigroup.com

Test conditions:
ISO 187:1990
(23 C + 1 C/RH 50% +2)