



## Advantage MF Lining

### Benefits

- Clean appearance
- 100% virgin softwood kraft fibres

### End-uses

- Interleaving



| PEFC | FSC | Quality Management System | Environmental Management System | Food Safety Regulations |
|------|-----|---------------------------|---------------------------------|-------------------------|
| •    | •   | ISO 9001:2015             | ISO 14001:2015                  | BFR, FDA, CONEG         |

| Technical Values   |                  |            |          |                |
|--------------------|------------------|------------|----------|----------------|
| Properties         |                  | Method     |          | Typical values |
| Basis Weight       | g/m <sup>2</sup> | ISO 536    |          | 50             |
| Thickness          | µm               | ISO 534    |          | 78             |
| Tensile strength   | kN/m             | ISO 1924-3 | MD<br>CD | 6,0<br>2,8     |
| Stretch            | %                | ISO 1924-3 | MD<br>CD | 2,2<br>7,5     |
| TEA                | J/m <sup>2</sup> | ISO 1924-3 | MD<br>CD | 80<br>150      |
| Tear strength      | mN               | ISO 1974   | MD<br>CD | 500<br>500     |
| Burst strength     | kPa              | ISO 2758   |          | 260            |
| Cobb <sub>60</sub> | g/m <sup>2</sup> | ISO 535    |          | 30             |



Issued from 01.01.2020,  
latest version available on  
[www.mondigroup.com](http://www.mondigroup.com)

**Test conditions:**  
ISO 187:1990  
(23 ± 1°C / RH 50 ± 2%)